

Agriculture
Landwirtschaft
Agricultura

334Z

Diameters Durchmesser Diâmetros	Tenacity Feinheitsfestigkeit Tenacidade	Linear Strength Reißfestigkeit Resistência Linear	Elongation Bruchdehnung Alongamento	Thermal shrinkage Heißluftschrimp Contração térmica 180°C
(mm)	(cN/tex)	(kg)	(%)	(%)
0.80	<i>Min. 36</i>	26	28.0 ± 3.0	<i>Min. 7.0</i>
1.00	<i>Min. 36</i>	40	28.0 ± 3.0	<i>Min. 8.0</i>
1.80	<i>Min. 30</i>	105	9.0 ± 3.0	<i>Min. 9.0</i>
2.00	<i>Min. 28</i>	125	9.0 ± 3.0	<i>Min. 9.0</i>
2.20	<i>Min. 26</i>	140	9.0 ± 3.0	<i>Min. 9.0</i>
2.40	<i>Min. 25</i>	155	8.0 ± 3.0	<i>Min. 8.0</i>
2.60	<i>Min. 25</i>	170	7.0 ± 3.0	<i>Min. 8.0</i>
2.80	<i>Min. 25</i>	210	7.0 ± 3.0	<i>Min. 8.0</i>
3.00	<i>Min. 25</i>	250	7.0 ± 3.0	<i>Min. 8.0</i>

Other dimensions available upon request.

(Revision: TB 8.2/165-10)

