



Tennis Strings
Tennissaiten
Raquetes de Ténis


372ML

Diameter Diâmetro Durchmesser (mm)	Linear Strength Resistência linear Lineare Festigkeit (N)	Knot Strength Resistência ao nó Knotenfestigkeit (N)	Loop Strength Resistência à laçada Schlingenfestigkeit (N)	Elongation Alongamento Bruchdehnung (%)	Thermal Shrinkage Contração Térmica Thermoschrumpf 180°C 30' (%)	Bending Stiffness Flexão Biegesteifigkeit (MPa)
1,20	Min. 380	Min. 280	Min. 730	30	12	13 - 16
1,24	Min. 400	Min. 300	Min. 770	30	12	13 - 16
1,25	Min. 400	Min. 300	Min. 770	31	12	13 - 16
1,28	Min. 420	Min. 320	Min. 810	32	12	13 - 16
1,29	Min. 420	Min. 320	Min. 810	32	12	13 - 16
1,30	Min. 420	Min. 320	Min. 810	32	12	13 - 16
1,32	Min. 420	Min. 320	Min. 810	32	12	13 - 16
1,35	Min. 440	Min. 340	Min. 850	32	12	13 - 16


TB 8.2/128-5

Profile Shape

Profilquerschnitt
Corte do Perfil



Heptagon
Siebener
Heptágono



Round
Rund
Redondo

Example

Beispiel
Exemplo

