



Tennis Strings
Tennissaiten
Raquetes de Ténis

374ML

C000 / C700

Diameter Diâmetro Durchmesser (mm)	Linear Strength Resistência linear Lineare Festigkeit (N)	Knot Strength Resistência ao nó Knotenfestigkeit (N)	Loop Strength Resistência à laçada Schlingenfestigkeit (N)	Elongation Alongamento Bruchdehnung (%)	Thermal Shrinkage Contração Térmica Thermoschrumpf 180°C 30' (%)	Bending Stiffness Flexão Biegesteifigkeit (MPa)
1,24 x 1,24	Min. 450	Min. 330	Min. 840	31	25	13 - 16
1,27 x 1,27	Min. 450	Min. 330	Min. 880	31	25	13 - 16
1,31 x 1,31	Min. 490	Min. 340	Min. 900	31	25	13 - 16


C114 / C753

Diameter Diâmetro Durchmesser (mm)	Linear Strength Resistência linear Lineare Festigkeit (N)	Knot Strength Resistência ao nó Knotenfestigkeit (N)	Loop Strength Resistência à laçada Schlingenfestigkeit (N)	Elongation Alongamento Bruchdehnung (%)	Thermal Shrinkage Contração Térmica Thermoschrumpf 180°C 30' (%)	Bending Stiffness Flexão Biegesteifigkeit (MPa)
1,31 x 1,31	Min. 450	Min. 330	Min. 870	21	25	13 - 16


TB 8.2/128-5

Profile Shape

Profilquerschnitt
Corte do Perfil



Heptagon
Siebener
Heptágono



Octagon
Achteck
Octágono

Example

Beispiel
Exemplo

